



## STI / Kings Plush Test Report Furniture Product Line

### Part Description

Product Line: Furniture    Contents    50% Polyester, 24% Cotton, 12% Rayon, 14% Linen

**Tybee Island**

Application: Upholstery    Finish:

Orientation \_\_\_\_\_

Repeat - V    24 3/8"  
Repeat - H    27 3/4"

Finished Weight:  
Finished Width:

Oz/yds2    10.6  
Inches    57.25

### Test Results

ASTM D-3597 Sec 7.4 ASTM D 4157	1. Abrasion Test:		
	Wyzenbeek:		51,000
	Wire Screen:		
ASTM D 3597 Sec 7.10 AATCC 16E	2. Colorfastness:		
	Light:	Grade	3.3
	Hours Exposed	Hours	40
ASTM D 3597 Sec 7.9 AATCC 8	3. Crocking	Dry	5
		Wet	5
ASTM D 3775	4. Fabric Construction:	EPI	
		PPI	42
ASTM D 5034-17	5. Tensile Strength:	Warp	207.9
		Filling	75.9
ASTM D2261-17	6. Tongue Tear Strength:	Warp	21.3
		Filling	12.1
ASTM D 4034-17	7. Seam Slippage:	Warp	73.5
		Filling	78.2
	8. Flammability:	Test	
		Rating	
		Filling	
JIFSC SECTION 4	9. Cleaning Code	Cleaning Code	WS

### Other Customer Requested tests:

UFAC	Rating	
CAL TB117-2013	Rating	Complies
ASTM D 4033 Dynamic Seam Fatigue Method		
ISO 12945-2 Pilling	Rating	4.5

Customer Requesting Test Data: **Whitewood Industries**

Contact Person

Request Date:

Response Date:    2/1/24

Special Comments: